



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	50-N2272G		50-N2250G		50-N160		50-N140		50-N110G		50-N092B		47-L442		48-L212Y		48-L185		47-L170Y		47-L171	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
1,1,2,2-Tetrachloroethane	79-34-5	31	2	31	2	14	1																
1-Methoxy-2-propylacetate	108-65-6					84	3																
2-Butanone (MEK)	78-93-3	15	1	15	1	9	0																
2-Butoxyethanol	111-76-2	>480	6	>480	6	>480	6																
2-Ethoxyethanol	110-80-5	247	5	247	5	166	4																
2-Ethoxyethyl acetate	111-15-9					92	3																
2-Nitropropane	79-46-9																						
2-Pentanone	107-87-9	22	1	22	1	11	1																
Acetaldehyde	75-07-0																						
Acetic acid, 10%	64-19-7							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Acetic acid, 20%	64-19-7							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Acetic acid, 25%	64-19-7	>480	6	>480	6			>480	6	>480	6	>480	6	>480	6	>480	6	270	5	>480	6	>480	6
Acetic acid, 99%	64-19-7																						
Acetic acid, glacial	64-19-7	160	4	160	4	66	3	125	4	60	3	30	2	>480	6	170	4	35	2	10	1	10	1
Acetone	67-64-1	0	0	0	0	6	0			2						2				2		2	2
Acetonitrile	75-05-8	4	0	4	0	12	1																
Acrylic acid	79-10-7					104	3																
Allyl alcohol	107-18-6					51	2																
Ammonia	7664-41-7																						
Ammonium Fluoride, 40%	12125-01-8																						
Ammonium hydroxide	1336-21-6					328	5																
Ammonium hydroxide, 25%	1336-21-6							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Amyl alcohol	71-41-0					>480	6																
Aniline (and homologs)	62-53-3																						
Aqua Regia	8007-56-5																						
Benzaldehyde, 99%	100-52-7																						
Benzene	101316-46-5					>480	6																
Butyrolactone, 99%	96-48-0																						
Carbon disulfide	75-15-0	22	1	22	1	12	1																
Carbon tetrachloride	56-23-5																						
Chlorine	7782-50-5					>480	6																
Chromic acid and chromates, 50%	1333-82-0 (CrO3)					>480	6																
Cirric Acid, 10%	77-92-9																						
Cyclohexane	110-82-7	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	75	3					10	1	10	1
Cyclohexanol	108-93-0	>480	6	>480	6	>480	6																
Cyclohexanone	108-94-1	92	3	92	3	52	2	23	1	18	1	10	1	256	5					10	1	10	1
Diacetone alcohol	123-42-2	164	4	164	4																		
Dibutyl phthalate	84-74-2	>480	6	>480	6																		

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 2 >30 MINUTES
- 3 >60 MINUTES
- 4 >120 MINUTES
- 5 >240 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	52-3670		52-3665		50-N2420GY		56-630		56-635		58-8657		58-8658D		58-8658K		57-8643R		57-8653R		57-8657R	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
1,1,2,2-Tetrachloroethane	79-34-5																						
1-Methoxy-2-propylacetate	108-65-6																						
2-Butanone (MEK)	78-93-3	<3	0																				
2-Butoxyethanol	111-76-2	25	1	63	3																		
2-Ethoxyethanol	110-80-5			58	5																		
2-Ethoxyethyl acetate	111-15-9	14	1	37	2																		
2-Nitropropane	79-46-9	12	1	26	1																		
2-Pentanone	107-87-9	6	0																				
Acetaldehyde	75-07-0	3	0	8	0																		
Acetic acid, 10%	64-19-7					>480	6																
Acetic acid, 20%	64-19-7					>480	6																
Acetic acid, 25%	64-19-7					>480	6																
Acetic acid, 99%	64-19-7	55	2	152	4																		
Acetic acid, glacial	64-19-7					100	3	60	3	60	3												
Acetone	67-64-1	9	0	11	1		1																
Acetonitrile	75-05-8	25	1	15	1			10	1	10	1												
Acrylic acid	79-10-7	44	2	66	3																		
Allyl alcohol	107-18-6																						
Ammonia	7664-41-7							10	1	10	1												
Ammonium Fluoride, 40%	12125-01-8	>480	6	>480	6																		
Ammonium hydroxide	1336-21-6	30	1	>440	5			0	0	0	0												
Ammonium hydroxide, 25%	1336-21-6					>480	6																
Amyl alcohol	71-41-0																						
Aniline (and homologs)	62-53-3	61	3	69	3																		
Aqua Regia	8007-56-5	>480	6	>480	6																		
Benzaldehyde, 99%	100-52-7	19	1																				
Benzene	101316-46-5																						
Butyrolactone, 99%	96-48-0			170	4																		
Carbon disulfide	75-15-0	<3	0																				
Carbon tetrachloride	56-23-5	12	1																				
Chlorine	7782-50-5																						
Chromic acid and chromates, 50%	1333-82-0 (CrO3)	15	1					120	4	120	4												
Citric Acid, 10%	77-92-9	>480	6	>480	6																		
Cyclohexane	110-82-7					10	1	240	5	240	5												
Cyclohexanol	108-93-0	146	4	392	5																		
Cyclohexanone	108-94-1					10	1	60	3	60	3												
Diacetone alcohol	123-42-2	84	3	96	3																		
Dibutyl phthalate	84-74-2	>480	6	>480	6																		

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	57-8615		57-8630R		57-8630		57-8640R		57-8645R		57-8645		57-8675								
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	
1,1,2,2-Tetrachloroethane	79-34-5																					
1-Methoxy-2-propylacetate	108-65-6																					
2-Butanone (MEK)	78-93-3																					
2-Butoxyethanol	111-76-2																					
2-Ethoxyethanol	110-80-5																					
2-Ethoxyethyl acetate	111-15-9																					
2-Nitropropane	79-46-9																					
2-Pentanone	107-87-9																					
Acetaldehyde	75-07-0																					
Acetic acid, 10%	64-19-7																					
Acetic acid, 20%	64-19-7																					
Acetic acid, 25%	64-19-7																					
Acetic acid, 99%	64-19-7																					
Acetic acid, glacial	64-19-7																					
Acetone	67-64-1																					
Acetonitrile	75-05-8																					
Acrylic acid	79-10-7																					
Allyl alcohol	107-18-6																					
Ammonia	7664-41-7																					
Ammonium Fluoride, 40%	12125-01-8																					
Ammonium hydroxide	1336-21-6																					
Ammonium hydroxide, 25%	1336-21-6																					
Amyl alcohol	71-41-0																					
Aniline (and homologs)	62-53-3																					
Aqua Regia	8007-56-5																					
Benzaldehyde, 99%	100-52-7																					
Benzene	101316-46-5																					
Butyrolactone, 99%	96-48-0																					
Carbon disulfide	75-15-0																					
Carbon tetrachloride	56-23-5																					
Chlorine	7782-50-5																					
Chromic acid and chromates, 50%	1333-82-0 (CrO3)																					
Citric Acid, 10%	77-92-9																					
Cyclohexane	110-82-7																					
Cyclohexanol	108-93-0																					
Cyclohexanone	108-94-1																					
Diacetone alcohol	123-42-2																					
Dibutyl phthalate	84-74-2																					

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	50-N2272G		50-N2250G		50-N160		50-N140		50-N110G		50-N092B		47-L442		48-L212Y		48-L185		47-L170Y		47-L171	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
Diesel Fuel						>480	6		6		6												
Diethylamine	109-89-7	23	1	23	1																		
Diethylene glycol	111-46-6					>480	6																
Diisobutyl ketone	108-83-8					>247	5																
Dimethyl acetamide	127-19-5	46	2	46	2	29	1																
Dimethylformamide	68-12-2																						
Dimethyl Sulphoxide	67-68-5					50	2																
Dioxane	123-91-1																						
Di-sec octyl phthalate	117-81-7																						
Epichlorohydrin	106-89-8																						
Ethanolamine	141-43-5	>480	6	>480	6																		
Ethidium bromide, 10%	1239-45-8																						
Ethyl acetate	141-78-6	20	1	20	1	13	1							72	3								
Ethyl alcohol	64-17-5	>480	6	>480	6	380	5	320	5	49	2	22	1	>480	6	>480	6	>480	6	>480	6	>480	6
Ethyl ether	60-29-7	21	1	21	1	32	2																
Ethyl Lactate	687-48-8	>480	6	>480	6													350	5				
Ethylamine	75-04-7					31	2																
Ethylene glycol	107-21-1	>480	6	>480	6	>480	6																
Formaldehyde, 37%	50-00-0					>480	6																
Formaldehyde, 99%	50-00-0																						
Formic acid	64-18-6																						
Freon	76-13-1																						
Furfural	98-01-1																						
Gasoline	8006-61-9					413	5																
Gasoline, white		>480	6	>480	6																		
Glutaraldehyde, 25%	111-30-8																						
Glutaraldehyde, 50%	111-30-8					>480	6																
Hexamethyldisilazane	999-97-3																						
Hexone	108-10-1																						
Hydrazene, 60%	7803-57-8					>480	6																
Hydrazine, 60%	302-01-2	>480	6	>480	6																		
Hydrazine, 65%	302-01-2																						
Hydrogen chloride	7647-01-0	>480	6	>480	6	>480	6																
Hydrogen chloride, 10%	7647-01-0							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Hydrogen chloride, 37%	7647-01-0							75	3	30	2	10	1	210	4	65	3	125	3				
Hydrogen fluoride	7664-39-3					190	4																
Hydrogen fluoride, 48%	7664-39-3																						
Hydrogen fluoride, 73%	7664-39-3																						

Chemical Permeation Guide [Updated 1/18/13]

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	52-3670		52-3665		50-N2420GY		56-630		56-635		58-8657		58-8658D		58-8658K		57-8643R		57-8653R		57-8657R	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
Diesel Fuel																							
Diethylamine	109-89-7								10	1	10	1											
Diethylene glycol	111-46-6																						
Diisobutyl ketone	108-83-8	23	1						60	3	60	3											
Dimethyl acetamide	127-19-5	36	2						30	2	30	2											
Dimethylformamide	68-12-2	40	2	38	2				10	1	10	1											
Dimethyl Sulphoxide	67-68-5			243	5																		
Dioxane	123-91-1	18	1																				
Di-sec octyl phthalate	117-81-7	>480	6	>480	6																		
Epichlorohydrin	106-89-8	15	1																				
Ethanolamine	141-43-5			>480	6																		
Ethidium bromide, 10%	1239-45-8								>480	6	>480	6											
Ethyl acetate	141-78-6	6	0	10	0				0	0	0	0											
Ethyl alcohol	64-17-5			73	3	>480	6																
Ethyl ether	60-29-7	<3	0	4	0				10	1	10	1											
Ethyl Lactate	687-48-8																						
Ethylamine	75-04-7																						
Ethylene glycol	107-21-1			>480	6																		
Formaldehyde, 37%	50-00-0																						
Formaldehyde, 99%	50-00-0			>480	6																		
Formic acid	64-18-6	250	5	>480	6				60	3	60	3											
Freon	76-13-1			160	4																		
Furfural	98-01-1	19	1	35	2																		
Gasoline	8006-61-9																						
Gasoline, white																							
Glutaraldehyde, 25%	111-30-8								>480	6	>480	6											
Glutaraldehyde, 50%	111-30-8																						
Hexamethyldisilazane	999-97-3	38	2	153	4																		
Hexone	108-10-1								10	1	10	1											
Hydrazene, 60%	7803-57-8																						
Hydrazine, 60%	302-01-2																						
Hydrazine, 65%	302-01-2			205	4																		
Hydrogen chloride	7647-01-0																						
Hydrogen chloride, 10%	7647-01-0			>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Hydrogen chloride, 37%	7647-01-0	25	1	>480	5	100	3	240	5	240	5												
Hydrogen fluoride	7664-39-3																						
Hydrogen fluoride, 48%	7664-39-3	>480	6	>480	6				120	4	120	4											
Hydrogen fluoride, 73%	7664-39-3								10	1	10	1											

Chemical Permeation Guide [Updated 1/18/13]

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	57-8615		57-8630R		57-8630		57-8640R		57-8645R		57-8645		57-8675								
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	
Diesel Fuel																						
Diethylamine	109-89-7																					
Diethylene glycol	111-46-6																					
Diisobutyl ketone	108-83-8																					
Dimethyl acetamide	127-19-5																					
Dimethylformamide	68-12-2																					
Dimethyl Sulphoxide	67-68-5																					
Dioxane	123-91-1																					
Di-sec octyl phthalate	117-81-7																					
Epichlorohydrin	106-89-8																					
Ethanolamine	141-43-5																					
Ethidium bromide, 10%	1239-45-8																					
Ethyl acetate	141-78-6																					
Ethyl alcohol	64-17-5																					
Ethyl ether	60-29-7																					
Ethyl Lactate	687-48-8																					
Ethylamine	75-04-7																					
Ethylene glycol	107-21-1																					
Formaldehyde, 37%	50-00-0																					
Formaldehyde, 99%	50-00-0																					
Formic acid	64-18-6																					
Freon	76-13-1																					
Furfural	98-01-1																					
Gasoline	8006-61-9																					
Gasoline, white																						
Glutaraldehyde, 25%	111-30-8																					
Glutaraldehyde, 50%	111-30-8																					
Hexamethyldisilazane	999-97-3																					
Hexone	108-10-1																					
Hydrazene, 60%	7803-57-8																					
Hydrazine, 60%	302-01-2																					
Hydrazine, 65%	302-01-2																					
Hydrogen chloride	7647-01-0																					
Hydrogen chloride, 10%	7647-01-0																					
Hydrogen chloride, 37%	7647-01-0																					
Hydrogen fluoride	7664-39-3																					
Hydrogen fluoride, 48%	7664-39-3																					
Hydrogen fluoride, 73%	7664-39-3																					

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES



CHEMICAL	CAS #	50-N2272G		50-N2250G		50-N160		50-N140		50-N110G		50-N092B		47-L442		48-L212Y		48-L185		47-L170Y		47-L171	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
Hydrogen peroxide, 30%	7722-84-1					>480	6																
Hydroquinone	123-31-9																						
Isobutyl alcohol	78-83-1																						
Iso-octane	540-84-1					>480	6																
Isopropyl alcohol	67-63-0	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Kerosene	8008-20-6					>480	6		6		6												
Lactic acid, 85%	598-82-3	>480	6	>480	6	>480	6																
Lauric acid, 36% in ethanol	143-07-7	219	4	219	4																		
Maleic acid, saturated	110-16-7	>480	6	>480	6	>480	6																
Methyl alcohol	67-56-1	40	2	40	2	68	3	65	3	22	1	21	1	32	2	20	1	45	2	15	1	15	1
Methyl Cellosolve®	109-86-4																						
Methyl chloroform	71-55-6	44	2	44	2	27	1																
Methyl methacrylate	80-62-6					22	1																
Methyl tert-butyl ether	1634-04-4					370	5																
Methylamine	74-89-5									1													
Methylamine 40%	74-89-5																						
Methylene chloride	75-09-2	2	0	2	0	3	0																
Mineral Oil/liquid paraffin						>480	6																
n-Amyl acetate	628-63-7					77	3																
Naphtha (coal tar)	8030-30-6					311	5																
Naphtha (Petroleum)	64742-48-9	>480	6	>480	6	>480	6																
n-Butyl acetate	123-86-4	33	2	33	2	57	2																
n-Butyl alcohol	71-36-3	>480	6	>480	6	>480	6	>480	6	350	5	130	4										
n-Heptan	142-85-5							>480	6														
n-Heptane	142-82-5	>480	6	>480	6	>480	6	>480	6	45	2	35	2	53	2								
n-Hexane	110-54-3	>480	6	>480	6	>480	6	>480	6	>480	6	260	5	50	2								
Nitric acid, 10%	7697-37-2							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Nitric acid, 40%	7697-37-2	>480	6	>480	6	>480	6	350	5	270	5	200	4	>480	6	>480	6	>480	6	>480	6	>480	6
Nitric acid, 70%	7697-37-2																						
Nitrobenzene	98-95-3					336	5																
Nitromethane	75-52-5																						
n-Pentane	109-66-0																						
n-Propyl acetate	109-60-4	68	3	68	3	14	1							75	3								
n-Propyl alcohol	71-23-8							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
n-Undecane	1120-21-4					>480	6																
Octyl alcohol	111-87-5	>480	6	>480	6	>480	6																
Oleic Acid	112-80-1																						
Oxalic acid, 12.5%	144-62-7																						

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 2 >30 MINUTES
- 3 >60 MINUTES
- 4 >120 MINUTES
- 5 >240 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	52-3670		52-3665		50-N2420GY		56-630		56-635		58-8657		58-8658D		58-8658K		57-8643R		57-8653R		57-8657R	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
Hydrogen peroxide, 30%	7722-84-1	>480	6	>480	6			>480	6	>480	6												
Hydroquinone	123-31-9			>480	6																		
Isobutyl alcohol	78-83-1	45	2	183	4																		
Iso-octane	540-84-1	17	1	92	3																		
Isopropyl alcohol	67-63-0	44	2	142	4	>480	6																
Kerosene	8008-20-6	30	1	100	3																		
Lactic acid, 85%	598-82-3	>480	6	>480	6																		
Lauric acid, 36% in ethanol	143-07-7	>480	6	>480	6																		
Maleic acid, saturated	110-16-7	>480	6	>480	6																		
Methyl alcohol	67-56-1	18	1	40	2	35	2					2		2		2		175	4	175	4	175	4
Methyl Cellosolve®	109-86-4			75	3																		
Methyl chloroform	71-55-6																						
Methyl methacrylate	80-62-6							10	1	10	1												
Methyl tert-butyl ether	1634-04-4							60	3	60	3												
Methylamine	74-89-5																						
Methylamine 40%	74-89-5			79	3																		
Methylene chloride	75-09-2							0	0	0	0												
Mineral Oil/liquid paraffin																							
n-Amyl acetate	628-63-7	13	1																				
Naphtha (coal tar)	8030-30-6																						
Naphtha (Petroleum)	64742-48-9																						
n-Butyl acetate	123-86-4	10	0					10	1	10	1												
n-Butyl alcohol	71-36-3	48	2	135	4																		
n-Heptan	142-85-5											2		2		2		121	4	121	4	121	4
n-Heptane	142-82-5							>480	6	>480	6												
n-Hexane	110-54-3			16	1			240	5	240	5												
Nitric acid, 10%	7697-37-2			>480	6	>480	6	>480	6	>480	6												
Nitric acid, 40%	7697-37-2					>480	6																
Nitric acid, 70%	7697-37-2	220	4	370	5			60	3	60	3												
Nitrobenzene	98-95-3	10	0																				
Nitromethane	75-52-5			22	1																		
n-Pentane	109-66-0			13	1																		
n-Propyl acetate	109-60-4																						
n-Propyl alcohol	71-23-8	58	2	75	3	>480	6	>480	6	>480	6												
n-Undecane	1120-21-4																						
Octyl alcohol	111-87-5	118	3	275	5																		
Oleic Acid	112-80-1	>480	6	>480	6																		
Oxalic acid, 12.5%	144-62-7	>480	6	>480	6																		

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	57-8615		57-8630R		57-8630		57-8640R		57-8645R		57-8645		57-8675								
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	
Hydrogen peroxide, 30%	7722-84-1																					
Hydroquinone	123-31-9																					
Isobutyl alcohol	78-83-1																					
Iso-octane	540-84-1																					
Isopropyl alcohol	67-63-0																					
Kerosene	8008-20-6																					
Lactic acid, 85%	598-82-3																					
Lauric acid, 36% in ethanol	143-07-7																					
Maleic acid, saturated	110-16-7																					
Methyl alcohol	67-56-1	75	3	97	3	75	3	97	3	97	3	97	3	75	3							
Methyl Cellosolve®	109-86-4																					
Methyl chloroform	71-55-6																					
Methyl methacrylate	80-62-6																					
Methyl tert-butyl ether	1634-04-4																					
Methylamine	74-89-5																					
Methylamine 40%	74-89-5																					
Methylene chloride	75-09-2																					
Mineral Oil/liquid paraffin																						
n-Amyl acetate	628-63-7																					
Naphtha (coal tar)	8030-30-6																					
Naphtha (Petroleum)	64742-48-9																					
n-Butyl acetate	123-86-4																					
n-Butyl alcohol	71-36-3																					
n-Heptan	142-85-5																					
n-Heptane	142-82-5	264	5	100	3	264	5	100	3	100	3	100	3	264	5							
n-Hexane	110-54-3																					
Nitric acid, 10%	7697-37-2																					
Nitric acid, 40%	7697-37-2																					
Nitric acid, 70%	7697-37-2																					
Nitrobenzene	98-95-3																					
Nitromethane	75-52-5																					
n-Pentane	109-66-0																					
n-Propyl acetate	109-60-4																					
n-Propyl alcohol	71-23-8																					
n-Undecane	1120-21-4																					
Octyl alcohol	111-87-5																					
Oleic Acid	112-80-1																					
Oxalic acid, 12.5%	144-62-7																					

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES



CHEMICAL	CAS #	50-N2272G		50-N2250G		50-N160		50-N140		50-N110G		50-N092B		47-L442		48-L212Y		48-L185		47-L170Y		47-L171	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
Palmitic Acid, Sat	57-10-3																						
Pentachlorophenol, 36% in Ethanol	87-86-5																						
Peracetic acid	79-21-0					65	3																
Perchloric acid, 60%	7601-90-3	>480	6	>480	6	>480	6																
Petrol, unleaded						>480	6		5		3												
Petroleum distillates (naphtha)	8002-05-9																						
Phenol, 90%	108-95-2					137	4																
Phosphoric acid, 85%	7664-38-2	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Piperazine, saturated	110-85-0					>480	6																
Potassium hydroxide, 50%	1310-58-3	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Propylene glycol	57-55-6					>480	6																
Propylene glycol monomethyl ether	107-98-2					129	4																
Pyridine	110-86-1	24	1	24	1																		
Sodium hydroxide, 20%	1310-73-2							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Sodium hydroxide, 40%	1310-73-2							>480	6	>480	6	150	4	>480	6	144	4	132	4	176	4	176	4
Sodium hydroxide, 50%	1310-73-2	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Sodium hypochlorite	7681-52-9							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Sodium hypochlorite, 13%	7681-52-9	>480	6	>480	6	>480	6																
Sodium silicate	6834-92-0	>480	6	>480	6			>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Stoddard solvent	8052-41-3																						
Sulfuric acid, 40%	7664-93-9							>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Sulfuric acid, 47%	7664-93-9																						
Sulfuric acid, 50%	7664-93-9	>480	6	>480	6			>480	6	350	4	240	4	>480	6	>480	6	>480	6	>480	6	>480	6
Sulfuric acid, 96%	7664-93-9	150	4	150	4	150	4	96	3	35	2	15	1	74	3	135	4	110	3	95	3	95	3
Tannic Acid, 65%	1401-55-4																						
Tetrachloroethylene	127-18-4					165	4																
Tetrahydrofuran	109-99-9					7	0																
Tetrapropene	68551-17-7	>480	6	>480	6	>480	6																
Thinner		14	1	14	1									39	2								
Toluene	108-88-3	39	2	39	2	21	1							54	3								
Triethanolamine	102-71-6	>480	6	>480	6			>480	6	>480	6												
Triethylamine	121-44-8					>480	6																
Turpentine	8006-64-2	>480	6	>480	6	>480	6																
VM & P Naphtha	8032-32-4					>480	6																
White Spirit	8052-40-13	>480	6	>480	6	>480	6																
Xylene	1330-20-7	115	3	115	3	40	2							185	4								

Chemical Permeation Guide [Updated 1/18/13]

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	52-3670		52-3665		50-N2420GY		56-630		56-635		58-8657		58-8658D		58-8658K		57-8643R		57-8653R		57-8657R	
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX
Palmitic Acid, Sat	57-10-3	>480	6	>480	6																		
Pentachlorophenol, 36% in Ethanol	87-86-5	>480	6	>480	6																		
Peracetic acid	79-21-0																						
Perchloric acid, 60%	7601-90-3	>480	6	>480	6			>480	6	>480	6												
Petrol, unleaded								60	3	60	3												
Petroleum distillates (naphtha)	8002-05-9			15	1																		
Phenol, 90%	108-95-2	84	3	108	3																		
Phosphoric acid, 85%	7664-38-2	>480	6	>480	6	>480	6	>480	6	>480	6												
Piperazine, saturated	110-85-0																						
Potassium hydroxide, 50%	1310-58-3			>480	6	>480	6	>480	6	>480	6												
Propylene glycol	57-55-6																						
Propylene glycol monomethyl ether	107-98-2																						
Pyridine	110-86-1	19	1																				
Sodium hydroxide, 20%	1310-73-2					>480	6					>480	6	>480	6	>480	6						
Sodium hydroxide, 40%	1310-73-2					>480	6					>480	6	>480	6	>480	6	>480	6	>480	6	>480	6
Sodium hydroxide, 50%	1310-73-2			>480	6	>480	6	>480	6	>480	6												
Sodium hypochlorite	7681-52-9					>480	6																
Sodium hypochlorite, 13%	7681-52-9																						
Sodium silicate	6834-92-0					>480	6																
Stoddard solvent	8052-41-3			62	3			>480	6	>480	6												
Sulfuric acid, 40%	7664-93-9					>480	6																
Sulfuric acid, 47%	7664-93-9	>480	6	>480	6			>480	6	>480	6												
Sulfuric acid, 50%	7664-93-9					>480	6																
Sulfuric acid, 96%	7664-93-9	180	4	260	5	95	3					2		1		1		>480	6	>480	6	>480	6
Tannic Acid, 65%	1401-55-4	>480	6	>480	6																		
Tetrachloroethylene	127-18-4																						
Tetrahydrofuran	109-99-9							0	0	0	0												
Tetrapropene	68551-17-7																						
Thinner																							
Toluene	108-88-3	9	0																				
Triethanolamine	102-71-6																						
Triethylamine	121-44-8																						
Turpentine	8006-64-2																						
VM & P Naphtha	8032-32-4			35	2																		
White Spirit	8052-40-13																						
Xylene	1330-20-7							10	1	10	1												

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES



PROTECTIVE INDUSTRIAL PRODUCTS



CHEMICAL	CAS #	57-8615		57-8630R		57-8630		57-8640R		57-8645R		57-8645		57-8675								
		BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	BTT	INDEX	
Palmitic Acid, Sat	57-10-3																					
Pentachlorophenol, 36% in Ethanol	87-86-5																					
Peracetic acid	79-21-0																					
Perchloric acid, 60%	7601-90-3																					
Petrol, unleaded																						
Petroleum distillates (naphtha)	8002-05-9																					
Phenol, 90%	108-95-2																					
Phosphoric acid, 85%	7664-38-2																					
Piperazine, saturated	110-85-0																					
Potassium hydroxide, 50%	1310-58-3																					
Propylene glycol	57-55-6																					
Propylene glycol monomethyl ether	107-98-2																					
Pyridine	110-86-1																					
Sodium hydroxide, 20%	1310-73-2																					
Sodium hydroxide, 40%	1310-73-2	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6	>480	6							
Sodium hydroxide, 50%	1310-73-2																					
Sodium hypochlorite	7681-52-9																					
Sodium hypochlorite, 13%	7681-52-9																					
Sodium silicate	6834-92-0																					
Stoddard solvent	8052-41-3																					
Sulfuric acid, 40%	7664-93-9																					
Sulfuric acid, 47%	7664-93-9																					
Sulfuric acid, 50%	7664-93-9																					
Sulfuric acid, 96%	7664-93-9	140	4	110	3	140	4	110	3	110	3	110	3	140	4							
Tannic Acid, 65%	1401-55-4																					
Tetrachloroethylene	127-18-4																					
Tetrahydrofuran	109-99-9																					
Tetrapropene	68551-17-7																					
Thinner																						
Toluene	108-88-3																					
Triethanolamine	102-71-6																					
Triethylamine	121-44-8																					
Turpentine	8006-64-2																					
VM & P Naphtha	8032-32-4																					
White Spirit	8052-40-13																					
Xylene	1330-20-7																					

Chemical Permeation Guide (Updated 1/18/13)

CAUTION: This guide is provided as an aid in determining the general suitability of various products for use with specific chemicals. These recommendations are advisory only and the SUITABILITY OF THE PRODUCT FOR A SPECIFIC APPLICATION OR ENVIRONMENT MUST BE DETERMINED BY THE PURCHASER OR USER OF THE PRODUCT. This document should be used as a guide only. Breakthrough Time (BTT) - The number of minutes from initial contact with a test chemical until it is first detected on the inside of the protective clothing. It is the number of minutes until your skin is exposed inside the gloves or other protective clothing.

- 1 >10 MINUTES
- 4 >60 MINUTES
- 5 >240 MINUTES
- 2 >30 MINUTES
- 3 >120 MINUTES
- 6 >480 MINUTES