

ISO/IEC 17025 Certified Third Party Test Report

DATE: August 11, 2020 **FILE:** WORPRO.A073120A
PO #: 149841
CLIENT: Worldwide Protective Products **ATTN:** Kathleen Shepherd
1409 Worldwide Lane
Wilkesboro, NC 28697

SAMPLE IDENTIFIED BY CLIENT AS:

Gloves Submitted
Name: R15 Rigger Glove
Style #: 87015
Color Red/Yellow/Black

TEST PROCEDURE:

	CONDUCTIVE & COMPRESSIVE HEAT RESISTANCE (CCHR) PER ASTM F1060, AS RECEIVED		THICKNESS PER ASTM D1777 OPTION 2
	TIME TO PAIN	TIME TO BURN	
	*****		*****
SPECIMEN 1	21.54 seconds	36.99 seconds	0.1447 in
SPECIMEN 2	22.09 seconds	38.40 seconds	0.1430 in
SPECIMEN 3	19.46 seconds	34.88 seconds	0.1420 in
SPECIMEN 4	19.82 seconds	36.33 seconds	0.1416 in
SPECIMEN 5	19.90 seconds	35.99 seconds	0.1436 in
*****	*****		*****
AVERAGE	20.56 seconds	36.52 seconds	0.1430 in

Plate Temperature: 500°F (260°C)

COMMENT: Test performed on glove palm only per client instruction.

Signed For The Company By

Joseph Lin
Laboratory Manager

JG/08



Stacy Sadowy
Quality Assurance Manager